



# TECHNICAL DATA

## BASIC SPECIALTIES

### WATER TABLE

	CASTING		RAMMING		GUNNING	TROWEL		DIP	
	Min.	Max.	Min.	Max.		Min.	Max.	Min.	Max.
BR-00042	4.5	5.5	3.5	4.5	*	*	*	*	*
BR-245			As Received			*	*	*	*
BR-97072	4.5	5.5	*	*	*	*	*	*	*
BR-98087	4.5	5.5	3.5	4.5	*	*	*	*	*
BR-99056	4.5	5.5	*	*	At Nozzle	*	*	*	*
BR-99073	5.0	5.3	*	*	*	*	*	*	*
CM95 -35	*	*	*	*	*	*	*	*	*
K/R BOND 95 A	*	*	*	*	*	18.0	20.0	18.0	22.0
K/R BOND 95 H	*	*	*	*	*	18.0	20.0	18.0	22.0
K/R CAST 98 AF	4.5	5.0	*	*	*	*	*	*	*
K/R GUN 165 AF	*	*	*	*	At Nozzle	*	*	*	*
K/R GUN 60 RG	*	*	*	*	At Nozzle	*	*	*	*
K/R GUN 91 A	*	*	*	*	At Nozzle	*	*	*	*
K/R GUN 91 G	*	*	*	*	At Nozzle	*	*	*	*
K/R INDUX 98	*	*	Installed dry		*	*	*	*	*
K/R PATCHBOND	*	*	*	*	*	9.0	11.0	*	*
LARCOBOND	*	*	*	*	*	23.0	25.0	23.0	27.0
N/R GUN 658	*	*	*	*	At Nozzle	*	*	*	*
N/R GUN 696	*	*	*	*	At Nozzle	*	*	*	*
N/R GUN 758	*	*	*	*	At Nozzle	*	*	*	*
N/R GUN 758C	*	*	*	*	At Nozzle	*	*	*	*
N/R GUN 796	*	*	*	*	At Nozzle	*	*	*	*
N/R GUN 91	*	*	*	*	At Nozzle	*	*	*	*
N/R GUN 98 AF	*	*	*	*	At Nozzle	*	*	*	*
N/R GUN LGM	*	*	*	*	At Nozzle	*	*	*	*
OCEANITE	Installed dry-NOT CAST OR RAMMED					*	*	*	*
PERMA HEARTH	*	*	Installed dry		*	*	*	*	*
PERMACAST FG GUN MIX	*	*	*	*	At Nozzle	*	*	*	*
PERMACAST FG HI STRENGTH	4.0	4.5	2.5	3.3	*	*	*	*	*
PERMACAST FG PLUS	3.0	4.5	*	*	*	*	*	*	*
PERMACAST FG RAM CAST	5.0	5.5	3.5	4.8	*	*	*	*	*
PERMAGUN 93 SG	*	*	*	*	At Nozzle	*	*	*	*
PERMAGUN S-I	*	*	*	*	At Nozzle	*	*	*	*
PERMAGUN S-II	*	*	*	*	At Nozzle	*	*	*	*
PERMANENTE 165 AF ALL PURPOSE	4.8	5.3	2.8	3.3	*	*	*	*	*
PERMANENTE 165 AF CASTABLE	4.5	5.0	2.8	3.3	*	*	*	*	*
PERMANENTE 165 AF RAM MIX	5.0	5.5	3.0	3.5	*	*	*	*	*
PERMANENTE 857 AF	5.0	5.5	3.0	3.5	At Nozzle	*	*	*	*
PERMANENTE 98 AF	4.5	5.0	2.5	3.0	*	*	*	*	*
PERMANENTE DRY	*	*	Installed dry		*	*	*	*	*



# TECHNICAL DATA

## BASIC SPECIALTIES

### WATER TABLE

	CASTING		RAMMING		GUNNING	TROWEL		DIP	
	Min.	Max.	Min.	Max.		Min.	Max.	Min.	Max.
PERMA-STAR 95	5.5	6.0	3.0	3.5	At Nozzle	*	*	*	*
PC-70 NOZZLE MIX	5.0	6.0	*	*	*	*	*	*	*
N/R RFG MORTAR	*	*	*	*	*	10.0	14.0	12.0	16.0
CORMAG LG	*	*	*	*	At Nozzle	*	*	*	*
EAFGUN 90P	*	*	*	*	At Nozzle	*	*	*	*
RESCOMAG GUN 90S	*	*	*	*	At Nozzle	*	*	*	*
RESCOMAG FG CASTABLE	5.0	5.5	*	*	*	*	*	*	*
RS-7003--S-0001	*	*	*	*	At Nozzle	*	*	*	*
EAFHEARTH 90	*	*	Installed dry		*	*	*	*	*
EAFPATCH 75	*	*	Installed dry		*	*	*	*	*
MAG CARBON DIP	*	*	*	*	*	*	*	Premixed	
MAG CARBON TROWEL	*	*	*	*	*	Premixed			
EXCELBOND D	*	*	*	*	*	23.0	25.0	23.0	27.0

\* NOT A RECOMMENDED INSTALLATION METHOD